

Product Description

Evero™ Natural Quartz Material is made from a blend of acrylic modified bio-based polyester resin, natural quartz, granite, and other exotic minerals. Evero has 25% pre-consumer recycled content.

Product Qualities

- Durable, long-lasting material
- Smooth, non-porous surface
- Easy to clean and maintain, absence of cracks or crevices prevent bacteria and mold from accumulating
- Chemical and stain resistant
- Impact and scratch resistant
- Repairable
- Resistant to heat and water damage
- 12 natural-looking colors available
- Homogenous composition allows for even distribution of color throughout material
- UV light resistant
- Inconspicuous seaming
- Standard thickness for 1/2"
- Available in shaped products

Care and Maintenance of Engineered Quartz

- For regular cleaning, use standard commercial or household products such as Formula 409® or Windex®.
- Remove tough stains, with non abrasive cleaners and pads such as a white Scotch Brite® and Lysol®.
- Refresh and restore the rich surface with a color enhancer such as Tenax® Ager, if needed.
- Avoid contact with harsh chemicals such as paint remover, bleach, acetone, etc.

Additional product literature available on the internet at bradleycorp.com.

- Use of brand names is intended only to indicate a type of cleaner. This does not constitute an endorsement. Nor does the omission of any brand name cleaner imply its inadequacy. Many products named are regional in distribution, and can be found in local supermarkets, department and hardware stores, or through your cleaning service.
- All products should be used in strict accordance with package instructions.

Physical Properties

| Physical Properties | Test Result | Test Method |
|----------------------------------|-----------------|-------------|
| Coefficient of Thermal Expansion | 23.86 ppm/°C | ASTM C-531 |
| Flexural Strength | 3267 psi | ASTM D790 |
| Flexural Modulus | 2086 ksi | ASTM D790 |
| Compressive Strength | 11,593 psi | ASTM C170 |
| Moisture Absorption | .065 % 24 hours | ASTM D570 |
| Hardness | 6-7 | Mohs Scale |
| Gloss (60°) | 40% minimum | Glossmeter |
| Fire Resistance, Flame & Smoke | Class 1 | ASTM E84 |
| Density | 2.2 g/cm3 | |

ANSI Standards

| Physical Properties | ANSI Test | Results |
|------------------------------|-----------|---------|
| Surface Integrity | 3.3 | Pass |
| Strength of Drain Connection | 4.2 | Pass |
| Impact Resistance | 4.3 | Pass |
| Load Resistance | 4.4 | Pass |
| Colorfastness | 5.1 | Pass |
| Stain Resistance | 5.2 | Pass |
| Chemical Resistance | 5.5 | Pass |
| Thermal Shock | 5.6 | Pass |